

PRL PC-GP2-TFE5

(PC+PTFE)

Polymer Resources, Ltd.

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	12.5	g/10min	ASTM D 1238
Temperature	300	°C	-
Load	1.2	kg	-
Mold Shrinkage, MD	0.0065	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	58.6	MPa	ASTM D 638
Tensile Strength at Break	58.6	MPa	ASTM D 638
Elongation at Break	10	%	ASTM D 638
Flexural Modulus	2413	MPa	ASTM D 790
Flexural Strength	93.1	MPa	ASTM D 790
Izod Impact notched, 1/8 in	160	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 66 psi	137	°C	ASTM D 648
DTUL @ 264 psi	131	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	1220	kg/m ³	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	118 - 124	°C	-
Pre-drying - Time	3 - 4	h	-
Melt temperature	316 - 343	°C	-
Mold temperature	82.2 - 116	°C	-
Zone 1	288 - 310	°C	-
Zone 2	299 - 321	°C	-
Zone 3	310 - 332	°C	-

Characteristics**Processing**

Injection Molding

Applications

General Purpose

Delivery form

Pellets

Regional Availability

North America