

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	125	MPa	ASTM D 638
Tensile Strength at Break	124	MPa	ASTM D 638
Elongation at Yield	2.3	%	ASTM D 638
Elongation at Break	2.3	%	ASTM D 638
Flexural Strength	179	MPa	ASTM D 790
Izod Impact notched, 1/8 in	43	J/m	ASTM D 256
Izod Impact unnotched, 1/8 in	370	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 264 psi	189	°C	ASTM D 648

Characteristics

Processing
Injection Molding

Regional Availability
Asia Pacific

Special Characteristics
Increased electrical conductivity