

**TORAYCA A630T-10V**

PPS-CF10

Toray Industries, Inc.

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Tensile Strength	<b>157</b>	MPa	ISO 527
Strain at break	<b>1.4</b>	%	ISO 527
Flexural modulus, 23°C	<b>10900</b>	MPa	ISO 178
Charpy notched impact strength, +23°C	<b>5.2</b>	kJ/m <sup>2</sup>	ISO 179/1eA

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Melting temperature, 10°C/min	<b>278</b>	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	<b>260</b>	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	<b>32</b>	E-6/K	ISO 11359-1/-2
Burning behav. at thickness h	<b>V-0</b>	class	IEC 60695-11-10

<b>Electrical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Volume resistivity	<b>10</b>	Ohm*m	IEC 62631-3-1

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>1380</b>	kg/m <sup>3</sup>	ISO 1183

**Characteristics****Special Characteristics**

Flame retardant

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America, Near East/Africa