

DIC-PPS CZ-1030

PPS-CF30

DIC Trading (USA) Inc.

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.0025	mm/mm	ASTM D 955
Mold Shrinkage, TD	0.011	mm/mm	ASTM D 955
Mechanical properties			
ASTM Data			
Tensile Modulus	10000	MPa	ASTM D 638
Tensile Strength	115	MPa	ASTM D 638
Elongation at Break	0.8	%	ASTM D 638
Compressive Strength	130	MPa	ASTM D 695
Flexural Modulus	9000	MPa	ASTM D 790
Flexural Strength	170	MPa	ASTM D 790
Rockwell Hardness	R 120	-	ASTM D 785
Izod Impact notched, 1/8 in	45	J/m	ASTM D 256
Izod Impact unnotched, 1/8 in	220	J/m	ASTM D 256
Thermal properties			
ASTM Data			
UL 94 Flame rating	V-0	-	UL 94
Thickness tested	0.8	mm	-
Coefficient of Thermal Expansion, MD	20	E-6/K	ASTM D 696
DTUL @ 264 psi	265	°C	ASTM D 648
Electrical properties			
ASTM Data			
Volume Resistivity	1E8	Ohm*cm	ASTM D 257
Other properties			
Water Absorption, 24hr	0.08	%	ASTM D 570
Density	1430	kg/m ³	ASTM D 792

Characteristics**Delivery form**

Black

Regional Availability

North America, Europe, Asia Pacific

Features

Tribologic Grade