

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	8000	MPa	ISO 527
Stress at break	125	MPa	ISO 527
Strain at break	2.1	%	ISO 527
Charpy notched impact strength, +23°C	8	kJ/m ²	ISO 179/1eA

Thermal properties	Value	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	280	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	240	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	29	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	49	E-6/K	ISO 11359-1/-2
Burning behav. at thickness h	V-0	class	IEC 60695-11-10
Thickness tested	0.4	mm	-

Electrical properties	Value	Unit	Test Standard
ISO Data			
Volume resistivity	1E14	Ohm*m	IEC 62631-3-1

Other properties	Value	Unit	Test Standard
Water absorption	0.02	%	Sim. to ISO 62
Density	1480	kg/m ³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	120 - 140	°C	-
Pre-drying - Time	4 - 8	h	-
Processing humidity	≤0.02	%	-
Melt temperature	320 - 340	°C	-
Mold temperature	140 - 180	°C	-
Injection pressure	<1	MPa	-

Characteristics

Processing

Injection Molding

Delivery form

Natural Color

Special Characteristics

Heat stabilized or stable to heat

Features

Laser Weldable

Chemical Resistance

General Chemical Resistance

Applications

Aircraft and Aerospace, Automotive, Electrical and Electronical, Encapsulation

Regional Availability

Europe