

RTP 1303 D

PPS-GF20

RTP Company

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.003	mm/mm	ASTM D 955
Mechanical properties			
ASTM Data			
Tensile Modulus	9239	MPa	ASTM D 638
Tensile Strength	124	MPa	ASTM D 638
Flexural Modulus	8963	MPa	ASTM D 790
Flexural Strength	179	MPa	ASTM D 790
Izod Impact notched, 1/8 in	64.1	J/m	ASTM D 256
Thermal properties			
ASTM Data			
UL 94 Flame rating	V-0	-	UL 94
Thickness tested	1.59	mm	-
DTUL @ 264 psi	260	°C	ASTM D 648
Electrical properties			
ASTM Data			
Dielectric Strength, Short Time	13.8	kV/mm	ASTM D 149
Dissipation Factor, 1 MHz	0.001	-	ASTM D 150
Dielectric Constant, 1 MHz	3.5	-	ASTM D 150
Volume Resistivity	>1E15	Ohm*cm	ASTM D 257
Arc Resistance	120	s	ASTM D 495
Other properties			
Density	1500	kg/m ³	ASTM D 792
Moisture Content	0.04	%	-
Processing Recommendation Injection Molding			
Pre-drying - Temperature	149	°C	-
Pre-drying - Time	6	h	-
Melt temperature	307 - 329	°C	-
Mold temperature	135 - 177	°C	-
Injection pressure	68.9 - 103	MPa	-

Characteristics**Processing**

Injection Molding

Regional Availability

North America, Europe, Asia Pacific