

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.0027	mm/mm	ASTM D 955
Mold Shrinkage, TD	0.012	mm/mm	ASTM D 955
Mechanical properties			
ASTM Data			
Tensile Modulus	11000	MPa	ASTM D 638
Tensile Strength	175	MPa	ASTM D 638
Elongation at Break	1.9	%	ASTM D 638
Compressive Strength	190	MPa	ASTM D 695
Flexural Modulus	10000	MPa	ASTM D 790
Flexural Strength	240	MPa	ASTM D 790
Rockwell Hardness	R 121	-	ASTM D 785
Izod Impact notched, 1/8 in	95	J/m	ASTM D 256
Izod Impact unnotched, 1/8 in	550	J/m	ASTM D 256
Thermal properties			
ASTM Data			
UL 94 Flame rating	V-0	-	UL 94
Thickness tested	0.8	mm	-
Coefficient of Thermal Expansion, MD	23	E-6/K	ASTM D 696
DTUL @ 264 psi	265	°C	ASTM D 648
Electrical properties			
ASTM Data			
Dielectric Strength, Short Time	16	kV/mm	ASTM D 149
Dissipation Factor, 1 MHz	0.002	-	ASTM D 150
Dielectric Constant, 1 MHz	4	-	ASTM D 150
Volume Resistivity	>1E15	Ohm*cm	ASTM D 257
Arc Resistance	120	s	ASTM D 495
Other properties			
Water Absorption, 24hr	0.02	%	ASTM D 570
Density	1560	kg/m ³	ASTM D 792

Characteristics

Delivery form

Black, Natural Color

Regional Availability

North America, Europe, Asia Pacific