

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	10000	MPa	ISO 527
^[C] Stress at break	145	MPa	ISO 527
^[C] Strain at break	2	%	ISO 527
^[C] Charpy notched impact strength, +23°C	10	kJ/m ²	ISO 179/1eA
^[C] Charpy notched impact strength, -30°C	9	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Temp. of deflection under load, 1.80 MPa	260	°C	ISO 75-1/-2

[C]: CAMPUS

Electrical properties	Value	Unit	Test Standard
ISO Data			
^[C] Volume resistivity	>1E13	Ohm*m	IEC 62631-3-1
^[C] Surface resistivity	1E11	Ohm	IEC 62631-3-2
^[C] Electric strength	21	kV/mm	IEC 60243-1

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Density	1500	kg/m ³	ISO 1183

[C]: CAMPUS