AXPOLY® PP51 1032

PP-X

Axion Polymers

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	**6**	g/10min	ISO 1133
Temperature	**230**	°C	-
Load	**2.16**	kg	-

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Strength	**20**	MPa	ISO 527
Flexural modulus, 23°C	**1100**	MPa	ISO 178
Izod notched impact strength, +23°C	**8**	kJ/m²	ISO 180/1A

Other properties	Value	Unit	Test Standard
Density	**990**	kg/m³	ISO 1183

Characteristics

Processing
Injection Molding

Delivery form
Black

Features
Copolymer

Certifications
Recycled Resin Content

Regional Availability
Europe

Copyright Altair Engineering GmbH. Altair Engineering GmbH assumes no liability for the system to be free of errors. The user takes sole responsibility for the use of this data under the exclusion of every liability from Altair Engineering GmbH; this is especially valid for claims of compensation resulting from consequential damages. Altair explicitly points out that any decision about the application of materials must be double checked with the producer of this material. This includes all contents of this system. Copyright laws are applicable for the content of this system.