LATICONTHER 52/11 CP3/600 F3

PP-X | LATI Industria Termoplastici S.p.A.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	**1.1**	%	ISO 294-4, 2577
Molding shrinkage, normal	**1.1**	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	**4700**	MPa	ISO 527
Stress at break	**20**	MPa	ISO 527
Strain at break	**1**	%	ISO 527
Charpy impact strength, +23°C	**4**	kJ/m²	ISO 179/1eU
Charpy notched impact strength, +23°C	**1**	kJ/m²	ISO 179/1eA

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	**100**	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	**130**	°C	ISO 75-1/-2
Vicat softening temperature, B	**115**	°C	ISO 306
Other Standards[S]			
Thermal Conductivity, solid state	**0.577**	W/(m K)	ASTM E 1461-92

S: These properties are reported by the producer according standards that are different to our defaults.

Electrical properties	Value	Unit	Test Standard
ASTM Data			
Surface Resistivity	**1E12**	Ohm	ASTM D 257

Other properties	Value	Unit	Test Standard
Density	**1430**	kg/m³	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	**80 - 90**	°C	-
Pre-drying - Time	**3**	h	-
Melt temperature	**230 - 250**	°C	-
Mold temperature	**30 - 60**	°C	-

Characteristics

Processing
Injection Molding

Special Characteristics
Thermally Conductive

Features
Homopolymer

Certifications
Food contact

Applications
Medical

Regional Availability
Europe

Copyright Altair Engineering GmbH. Altair Engineering GmbH assumes no liability for the system to be free of errors. The user takes sole responsibility for the use of this data under the exclusion of every liability from Altair Engineering GmbH; this is especially valid for claims of compensation resulting from consequential damages. Altair explicitly points out that any decision about the application of materials must be double checked with the producer of this material. This includes all contents of this system. Copyright laws are applicable for the content of this system.