

## Polywood P 70 PP2 A3

PP-X

Grade is obsolete.

Advanced Compounding GmbH & Co. KG

### Product Texts

For more detailed information, please read our or contact our representatives in your region.

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	8200	MPa	ISO 527
Tensile Strength	28	MPa	ISO 527
Strain at break	0.45	%	ISO 527
Flexural modulus, 23°C	9400	MPa	ISO 178
Charpy impact strength, +23°C	3.37	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	2.31	kJ/m <sup>2</sup>	ISO 179/1eA

Other properties	Value	Unit	Test Standard
Density	1200	kg/m <sup>3</sup>	ISO 1183

### Characteristics

#### Delivery form

Pellets

#### Regional Availability

Europe