

Supol HT125E

PP-X

LyondellBasell Industries

Product Texts

Supol materials are produced under licence of Hyundai Engineering Plastics, Korea Ltd.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	25	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Flexural modulus, 23°C	1850	MPa	ISO 178
Izod notched impact strength, +23°C	13	kJ/m ²	ISO 180/1A

Other properties	Value	Unit	Test Standard
Density	970	kg/m ³	ISO 1183

Characteristics

Processing

Injection Molding

Special Characteristics

U.V. stabilized or stable to weather

Features

Copolymer

Applications

Automotive

Regional Availability

Europe