

## Supol HT345E

PP-X

LyondellBasell Industries

### Product Texts

Supol materials are produced under licence of Hyundai Engineering Plastics, Korea Ltd.

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	27	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Flexural modulus, 23°C	2150	MPa	ISO 178
Izod notched impact strength, +23°C	9	kJ/m <sup>2</sup>	ISO 180/1A

Other properties	Value	Unit	Test Standard
Density	1050	kg/m <sup>3</sup>	ISO 1183

### Characteristics

#### Processing

Injection Molding

#### Special Characteristics

High impact or impact modified, U.V. stabilized or stable to weather

#### Features

Copolymer

#### Applications

Automotive

#### Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa