

ML 71 BG natural

PP-X30

Omikron

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	7	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Yield stress	55	MPa	ISO 527
Flexural modulus, 23°C	4000	MPa	ISO 178
Izod notched impact strength, +23°C	6	kJ/m ²	ISO 180/1A

Characteristics**Delivery form**

Natural Color

Regional Availability

Europe