

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	14	g/10min	ASTM D 1238
Mold Shrinkage, MD	0.014	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Modulus	1100	MPa	ASTM D 638
Tensile Strength at Yield	26	MPa	ASTM D 638
Tensile Strength at Break	200	MPa	ASTM D 638
Flexural Modulus	1200	MPa	ASTM D 790
Flexural Strength	33	MPa	ASTM D 790

Thermal properties	Value	Unit	Test Standard
ASTM Data			
UL 94 Flame rating	V-2	-	UL 94
Thickness tested	1.6	mm	-
DTUL @ 66 psi	78	°C	ASTM D 648
DTUL @ 264 psi	48	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	955	kg/m ³	ASTM D 792

Characteristics

Special Characteristics

Flame retardant

Regional Availability

North America

Features

Copolymer