

**Product Texts**

Filler: 30 % Scallop

**Mechanical properties****Value****Unit****Test Standard****ISO Data**

Tensile Modulus

**1550**

MPa

ISO 527

Strain at break

**9.6**

%

ISO 527

Charpy impact strength, +23°C

**7.6**kJ/m<sup>2</sup>

ISO 179/1eU

**Characteristics****Processing**

Injection Molding

**Applications**

Packaging

**Certifications**

Contains renewable resources

**Regional Availability**

Europe