

Meplen EC B40

PP-Z40

Mepol S.r.l.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	12	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Molding shrinkage, parallel	1.0	%	ISO 294-4, 2577
Mechanical properties			
ISO Data			
Yield stress	22	MPa	ISO 527
Strain at break	30	%	ISO 527
Flexural modulus, 23°C	1700	MPa	ISO 178
Izod notched impact strength, +23°C	3.8	kJ/m ²	ISO 180/1A
Izod notched impact strength	2.5	kJ/m ²	ISO 180/1A
Temperature	0	°C	-
Shore D hardness	70	-	ISO 7619-1
Thermal properties			
ISO Data			
Melting temperature, 10°C/min	165	°C	ISO 11357-1/-3
Vicat softening temperature, B	90	°C	ISO 306
Other properties			
Density	1360	kg/m ³	ISO 1183

Characteristics**Special Characteristics**

Anti-static, U.V. stabilized or stable to weather, Heat stabilized or stable to heat

Regional Availability

Europe

Features

Copolymer