

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	<b>10</b>	g/10min	ISO 1133
Temperature	<b>230</b>	°C	-
Load	<b>2.16</b>	kg	-

Other properties	Value	Unit	Test Standard
Density	<b>1620</b>	kg/m <sup>3</sup>	ISO 1183

Processing Recommendation Extrusion	Value	Unit	Test Standard
Pre-drying - Temperature	<b>90</b>	°C	-
Pre-drying - Time	<b>6</b>	h	-
Feed temperature	<b>300</b>	°C	-
Zone 1	<b>200</b>	°C	-
Zone 2	<b>240</b>	°C	-
Zone 3	<b>290</b>	°C	-
Zone 4	<b>300</b>	°C	-
Zone 5	<b>300</b>	°C	-
Nozzle temperature	<b>300</b>	°C	-

**Characteristics**

**Processing**

Film Extrusion, Other Extrusion

**Certifications**

Food contact

**Features**

Blending Resin

**Regional Availability**

Europe