

PRS 110 black

PP-Z50

Omikron

Product Texts

Barium Sulphate Filled

Processing/Physical Characteristics**Value****Unit****Test Standard****ISO Data**

Melt flow index, MFI

6

g/10min

ISO 1133

Temperature

230

°C

-

Load

2.16

kg

-

Mechanical properties**Value****Unit****Test Standard****ISO Data**

Yield stress

15

MPa

ISO 527

Flexural modulus, 23°C

1500

MPa

ISO 178

Izod notched impact strength, +23°C

3kJ/m²

ISO 180/1A

Characteristics**Delivery form**

Black

Regional Availability

Europe