

## Polywood RIC 60 PP 10091

PP-Z60

Grade is obsolete.

Advanced Compounding GmbH & Co. KG

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	12.5	g/10min	ISO 1133
Temperature	230	°C	-
Load	5	kg	-
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Tensile Modulus	1990	MPa	ISO 527
Tensile Strength	25.8	MPa	ISO 527
Charpy impact strength, +23°C	15.5	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	4.79	kJ/m <sup>2</sup>	ISO 179/1eA
<b>Other properties</b>			
Density	1140	kg/m <sup>3</sup>	ISO 1183

### Characteristics

#### Processing

Injection Molding

#### Delivery form

Pellets

#### Certifications

Contains renewable resources

#### Applications

Automotive

#### Regional Availability

Europe