

**QG 140 black**

PP-Z65

Omikron

**Product Texts**

Barium Sulphate Filled

**Processing/Physical Characteristics**

	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Melt flow index, MFI	<b>3</b>	g/10min	ISO 1133
Temperature	<b>230</b>	°C	-
Load	<b>2.16</b>	kg	-

**Mechanical properties**

	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Yield stress	<b>30</b>	MPa	ISO 527
Flexural modulus, 23°C	<b>3000</b>	MPa	ISO 178
Izod notched impact strength, +23°C	<b>2</b>	kJ/m <sup>2</sup>	ISO 180/1A

**Characteristics****Delivery form**

Black

**Regional Availability**

Europe

**Features**

Acoustical Barrier Properties