

Product Texts

Barium Sulphate Filled

Processing/Physical Characteristics

ISO Data

	Value	Unit	Test Standard
Melt flow index, MFI	3	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties

ISO Data

	Value	Unit	Test Standard
Yield stress	30	MPa	ISO 527
Flexural modulus, 23°C	3000	MPa	ISO 178
Izod notched impact strength, +23°C	2	kJ/m ²	ISO 180/1A

Characteristics

Delivery form

Natural Color

Regional Availability

Europe

Features

Acoustical Barrier Properties