

4PROP 9D21275

PP-Z75

4Plas

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	0.5	%	ISO 294-4, 2577
Molding shrinkage, normal	0.5	%	ISO 294-4, 2577

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	7500	MPa	ISO 527
Stress at break	25	MPa	ISO 527
Izod notched impact strength, +23°C	4	kJ/m ²	ISO 180/1A
Izod notched impact strength	3	kJ/m ²	ISO 180/1A
Temperature	-30	°C	-

Thermal properties	Value	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	167	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	75	°C	ISO 75-1/-2
Burning behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.6	mm	-
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	0.8	mm	-

Other properties	Value	Unit	Test Standard
Density	2270	kg/m ³	ISO 1183
Moisture Content	0.1	%	-

Characteristics**Features**

Homopolymer

Regional Availability

Europe