

4PROP 9C19300

PP

4Plas

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	9	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ISO Data			
Tensile Modulus	1300	MPa	ISO 527
Stress at break	20	MPa	ISO 527
Strain at break	10	%	ISO 527
Izod notched impact strength, +23°C	25	kJ/m ²	ISO 180/1A
Izod notched impact strength	13	kJ/m ²	ISO 180/1A
Temperature	-30	°C	-
Thermal properties			
ISO Data			
Melting temperature, 10°C/min	165	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	45	°C	ISO 75-1/-2
Burning behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.6	mm	-
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	0.8	mm	-
Electrical properties			
ISO Data			
Volume resistivity	10	Ohm*m	IEC 62631-3-1
Surface resistivity	1000	Ohm	IEC 62631-3-2
Other properties			
Density	1000	kg/m ³	ISO 1183

Characteristics**Special Characteristics**

Increased electrical conductivity

Regional Availability

Europe

Features

Copolymer