

**4PROP 9D13300 H**

PP

4Plas

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Melt flow index, MFI	<b>10</b>	g/10min	ISO 1133
Temperature	<b>230</b>	°C	-
Load	<b>2.16</b>	kg	-
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Tensile Modulus	<b>2000</b>	MPa	ISO 527
Stress at break	<b>25</b>	MPa	ISO 527
Izod notched impact strength, +23°C	<b>4</b>	kJ/m <sup>2</sup>	ISO 180/1A
Izod notched impact strength	<b>3</b>	kJ/m <sup>2</sup>	ISO 180/1A
Temperature	<b>-30</b>	°C	-
<b>Thermal properties</b>			
<b>ISO Data</b>			
Melting temperature, 10°C/min	<b>165</b>	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	<b>55</b>	°C	ISO 75-1/-2
Burning behav. at 1.5 mm nom. thickn.	<b>V-2</b>	class	IEC 60695-11-10
Thickness tested	<b>1.6</b>	mm	-
Burning behav. at thickness h	<b>V-2</b>	class	IEC 60695-11-10
Thickness tested	<b>3.2</b>	mm	-
<b>Electrical properties</b>			
<b>ISO Data</b>			
Volume resistivity	<b>1E13</b>	Ohm*m	IEC 62631-3-1
Surface resistivity	<b>1E15</b>	Ohm	IEC 62631-3-2
Comparative tracking index	<b>600</b>	-	IEC 60112
<b>Other properties</b>			
Density	<b>1000</b>	kg/m <sup>3</sup>	ISO 1183

**Characteristics****Special Characteristics**

Heat stabilized or stable to heat

**Regional Availability**

Europe

**Features**

Homopolymer