

6D20

PP

Braskem

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	1.9	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	27	MPa	ASTM D 638
Elongation at Yield	10	%	ASTM D 638
Izod Impact notched, 1/8 in	59	J/m	ASTM D 256

Characteristics**Processing**

Film Extrusion, Blow Molding

Certifications

Food contact, Food approval FDA 21 CFR

Features

Low Odor, Copolymer, Random Copolymer

Regional Availability

North America, Europe