

23S1Acs256

PP

Invista

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	2	g/10min	ASTM D 1238

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	29	MPa	ASTM D 638
Elongation at Yield	11	%	ASTM D 638
Flexural Modulus	1040	MPa	ASTM D 790
Rockwell Hardness	R 90	-	ASTM D 785
Gardner Impact	36	J	ASTM D 2794,4226,5420
Izod Impact notched, 1/8 in	62	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 66 psi	91	°C	ASTM D 648
Melting Temperature	153	°C	ASTM D 3418

Other properties	Value	Unit	Test Standard
Density	900	kg/m ³	ASTM D 792

Characteristics**Processing**

Blow Molding

Features

Copolymer, Random Copolymer

Certifications

Food contact, Food approval FDA 21 CFR, Medical Grade, US Pharmacopeia Class VI Approved, Drug Master File, RoHS compliant

Applications

Medical

Regional Availability

North America