

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	9	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	1200	MPa	ISO 527
Yield stress	24	MPa	ISO 527
Yield strain	4	%	ISO 527
Strain at break	10	%	ISO 527
Charpy notched impact strength, +23°C	5.5	kJ/m ²	ISO 179/1eA
Izod impact strength, +23°C	35	kJ/m ²	ISO 180/1U
Izod notched impact strength, +23°C	6	kJ/m ²	ISO 180/1A

Other properties	Value	Unit	Test Standard
Density	920	kg/m ³	ISO 1183

Characteristics

Processing

Injection Molding

Delivery form

Black

Features

Copolymer

Certifications

Recycled Resin Content

Applications

General Purpose

Regional Availability

Europe