

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	22.5	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ISO Data			
Flexural modulus	1300	MPa	ISO 178
Charpy notched impact strength, +23°C	7	kJ/m ²	ISO 179/1eA
Other properties			
Density	920	kg/m ³	ISO 1183
Moisture Content	0.1	%	-

Characteristics

Delivery form

Black

Certifications

Recycled Resin Content

Features

Copolymer

Regional Availability

Europe