

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	11	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Other properties			
Density	1070	kg/m ³	ISO 1183
Moisture Content	0.1	%	-

Characteristics

Delivery form

Black

Regional Availability

Europe

Certifications

Recycled Resin Content