

**100-GA35**

PP

INEOS Olefins &amp; Polymers

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	35	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Yield stress	31	MPa	ISO 527
Flexural modulus, 23°C	1350	MPa	ISO 178
Charpy notched impact strength, +23°C	2.3	kJ/m <sup>2</sup>	ISO 179/1eA
Izod notched impact strength, +23°C	3.3	kJ/m <sup>2</sup>	ISO 180/1A
<b>Thermal properties</b>			
<b>ISO Data</b>			
Temp. of deflection under load, 0.45 MPa	78	°C	ISO 75-1/-2

**Characteristics****Processing**

Injection Molding, Other Extrusion, Coating

**Regional Availability**

Europe

**Features**

Blending Resin, Homopolymer