

Product Texts

BOPP film applications.
Metallisation applications.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	2	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Yield stress	31	MPa	ISO 527
Flexural modulus, 23°C	1450	MPa	ISO 178

Thermal properties	Value	Unit	Test Standard
ASTM Data			
Melting Temperature	162	°C	ASTM D 3418

Characteristics**Features**

Barrier Properties, Good Adhesion, Low Odor, Homopolymer

Regional Availability

Europe

Applications

Packaging