

**Product Texts**

BOPP film applications.  
Metallisation applications.

| Processing/Physical Characteristics | Value | Unit    | Test Standard |
|-------------------------------------|-------|---------|---------------|
| <b>ISO Data</b>                     |       |         |               |
| Melt flow index, MFI                | 3     | g/10min | ISO 1133      |
| Temperature                         | 230   | °C      | -             |
| Load                                | 2.16  | kg      | -             |

| Mechanical properties  | Value | Unit | Test Standard |
|------------------------|-------|------|---------------|
| <b>ISO Data</b>        |       |      |               |
| Yield stress           | 29    | MPa  | ISO 527       |
| Flexural modulus, 23°C | 1450  | MPa  | ISO 178       |

| Thermal properties  | Value | Unit | Test Standard |
|---------------------|-------|------|---------------|
| <b>ASTM Data</b>    |       |      |               |
| Melting Temperature | 162   | °C   | ASTM D 3418   |

**Characteristics****Features**

Barrier Properties, Good Adhesion, Low Odor, Homopolymer

**Regional Availability**

Europe

**Applications**

Packaging