

**Product Texts**

BOPP film applications.

**Processing/Physical Characteristics****Value****Unit****Test Standard****ISO Data**

Melt flow index, MFI	8	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

**Mechanical properties****Value****Unit****Test Standard****ISO Data**

Yield stress	32	MPa	ISO 527
Flexural modulus, 23°C	1450	MPa	ISO 178
Charpy notched impact strength, +23°C	3.3	kJ/m <sup>2</sup>	ISO 179/1eA
Izod notched impact strength, +23°C	4	kJ/m <sup>2</sup>	ISO 180/1A

**Thermal properties****Value****Unit****Test Standard****ASTM Data**

Melting Temperature	161	°C	ASTM D 3418
---------------------	-----	----	-------------

**Characteristics****Processing**

Thermoforming

**Applications**

General Purpose, Packaging

**Features**

Low Odor, Homopolymer

**Regional Availability**

Europe