

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	9	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ISO Data			
Yield stress	32	MPa	ISO 527
Flexural modulus, 23°C	1450	MPa	ISO 178
Izod notched impact strength, +23°C	3.5	kJ/m ²	ISO 180/1A
Izod notched impact strength	3.4	kJ/m ²	ISO 180/1A
Temperature	0	°C	-
Thermal properties			
ISO Data			
Temp. of deflection under load, 0.45 MPa	103	°C	ISO 75-1/-2

Characteristics

Processing

Film Extrusion

Features

Homopolymer

Additives

Lubricants, Antiblocking agent, Release agent

Regional Availability

Europe