

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	12	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Yield stress	34	MPa	ISO 527
Flexural modulus, 23°C	1400	MPa	ISO 178

Characteristics

Features

Gas Fading Resistance, Low Odor, Homopolymer

Regional Availability

Europe