

Product Texts

Fibre applications.

Processing/Physical Characteristics

	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	25	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties

	Value	Unit	Test Standard
ISO Data			
Yield stress	33	MPa	ISO 527
Flexural modulus, 23°C	1400	MPa	ISO 178

Characteristics**Features**

Gas Fading Resistance, Low Odor, Homopolymer

Regional Availability

Europe