

Product Texts

Fibre grade for high speed spinning process.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	25	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

Thermal properties	Value	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	160	°C	ISO 11357-1/-3

Characteristics**Features**

Gas Fading Resistance, Homopolymer

Regional Availability

Europe