

Product Texts

BOPP film applications.
Metallisable film applications.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	8	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Yield stress	32	MPa	ISO 527
Flexural modulus, 23°C	1450	MPa	ISO 178
Charpy notched impact strength, +23°C	3.3	kJ/m ²	ISO 179/1eA
Izod notched impact strength, +23°C	4	kJ/m ²	ISO 180/1A

Thermal properties	Value	Unit	Test Standard
ASTM Data			
Melting Temperature	161	°C	ASTM D 3418

Characteristics**Processing**

Thermoforming

Features

Low Odor, Homopolymer

Applications

General Purpose, Packaging

Regional Availability

Europe