

Product Texts

Coextruded bioriented film using the tenter process.

| Processing/Physical Characteristics | Value | Unit | Test Standard |
|--|--------------|-------------|----------------------|
| ISO Data | | | |
| Melt flow index, MFI | 2 | g/10min | ISO 1133 |
| Temperature | 230 | °C | - |
| Load | 2.16 | kg | - |
| Mechanical properties | | | |
| ISO Data | | | |
| Yield stress | 31 | MPa | ISO 527 |
| Flexural modulus, 23°C | 1350 | MPa | ISO 178 |
| Thermal properties | | | |
| ASTM Data | | | |
| Melting Temperature | 158 | °C | ASTM D 3418 |

Characteristics**Features**

Homopolymer

Regional Availability

Europe