

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	2	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ISO Data			
Yield stress	27	MPa	ISO 527
Flexural modulus, 23°C	950	MPa	ISO 178
Izod notched impact strength, +23°C	10	kJ/m ²	ISO 180/1A
Thermal properties			
ISO Data			
Melting temperature, 10°C/min	149	°C	ISO 11357-1/-3

Characteristics

Processing

Sheet Extrusion, Other Extrusion, Thermoforming

Features

Blush Resistance/Low Crease Whitening, Color Stability, Melt Strength, Thermal Stability, Copolymer, Random Copolymer

Applications

General Purpose

Regional Availability

Europe