

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	3.8	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ISO Data			
Yield stress	26	MPa	ISO 527
Flexural modulus, 23°C	950	MPa	ISO 178
Izod notched impact strength, +23°C	8	kJ/m ²	ISO 180/1A
Thermal properties			
ASTM Data			
Melting Temperature	145	°C	ASTM D 3418

Characteristics

Processing

Sheet Extrusion, Thermoforming

Features

Blush Resistance/Low Crease Whitening, Color Stability, Thermal Stability, Copolymer, Random Copolymer

Applications

General Purpose

Regional Availability

Europe