

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	1.9	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Yield stress	26	MPa	ISO 527
Flexural modulus, 23°C	1150	MPa	ISO 178
Charpy notched impact strength, +23°C	7	kJ/m <sup>2</sup>	ISO 179/1eA

## Characteristics

### Processing

Blow Molding

### Certifications

Food contact

### Special Characteristics

Heat stabilized or stable to heat, Transparent

### Applications

Packaging

### Features

High Gloss, Copolymer, Random Copolymer

### Regional Availability

Europe