

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	13	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Yield stress	27	MPa	ISO 527
Flexural modulus, 23°C	850	MPa	ISO 178
Charpy notched impact strength, +23°C	8	kJ/m <sup>2</sup>	ISO 179/1eA
<b>Thermal properties</b>			
<b>ISO Data</b>			
Temp. of deflection under load, 0.45 MPa	70	°C	ISO 75-1/-2

### Characteristics

#### Processing

Injection Molding

#### Additives

Release agent

#### Special Characteristics

Anti-static, High impact or impact modified, Transparent

#### Features

High Gloss, Nucleated, Copolymer, Random Copolymer

#### Certifications

Food contact

#### Applications

Packaging

#### Regional Availability

Europe