

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	1.5	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	900	MPa	ISO 527
Yield stress	24	MPa	ISO 527
Charpy notched impact strength, +23°C	20	kJ/m <sup>2</sup>	ISO 179/1eA

## Characteristics

### Processing

Blow Molding

### Special Characteristics

Transparent

### Features

High Gloss, Thermal Stability, Copolymer, Random Copolymer

### Chemical Resistance

General Chemical Resistance

### Regional Availability

Europe