

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	25	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Yield stress	29	MPa	ISO 527
Flexural modulus, 23°C	1550	MPa	ISO 178
Izod notched impact strength, +23°C	7	kJ/m <sup>2</sup>	ISO 180/1A
Izod notched impact strength	4.5	kJ/m <sup>2</sup>	ISO 180/1A
Temperature	-20	°C	-
<b>Thermal properties</b>			
<b>ISO Data</b>			
Temp. of deflection under load, 0.45 MPa	108	°C	ISO 75-1/-2

### Characteristics

#### Processing

Injection Molding

#### Special Characteristics

Anti-static, High impact or impact modified

#### Features

Low Warpage, Nucleated, Copolymer, Impact Copolymer

#### Applications

Toys

#### Regional Availability

Europe