

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	55	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ISO Data			
Yield stress	24	MPa	ISO 527
Flexural modulus, 23°C	1100	MPa	ISO 178
Charpy notched impact strength, +23°C	5.2	kJ/m ²	ISO 179/1eA
Izod notched impact strength, +23°C	6	kJ/m ²	ISO 180/1A
Thermal properties			
ISO Data			
Temp. of deflection under load, 0.45 MPa	90	°C	ISO 75-1/-2

Characteristics

Processing

Injection Molding

Special Characteristics

Anti-static, High impact or impact modified

Features

High Crystallinity, Low Warpage, Nucleated, Copolymer, Impact Copolymer

Certifications

Food contact

Applications

Packaging

Regional Availability

Europe