

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	8	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Flexural modulus, 23°C	1100	MPa	ISO 178
Izod notched impact strength	8	kJ/m <sup>2</sup>	ISO 180/1A
Temperature	-20	°C	-

## Characteristics

### Processing

Injection Molding

### Special Characteristics

High impact or impact modified

### Features

Low Warpage, Copolymer, Impact Copolymer

### Certifications

Food contact, Food approval FDA 21 CFR

### Applications

Toys

### Regional Availability

Europe