

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	20	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Flexural modulus, 23°C	1000	MPa	ISO 178
Izod notched impact strength	10	kJ/m ²	ISO 180/1A
Temperature	-20	°C	-

Characteristics

Processing

Injection Molding

Special Characteristics

High impact or impact modified

Features

Low Warpage, Copolymer, Impact Copolymer

Certifications

Food contact

Applications

Automotive

Regional Availability

Europe