

5135I2

PP

Pinnacle Polymers LLC

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	35	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ASTM Data			
Tensile Strength at Yield	25.5	MPa	ASTM D 638
Elongation at Yield	12	%	ASTM D 638
Izod Impact notched, 1/8 in	58.7	J/m	ASTM D 256
Thermal properties			
ASTM Data			
Melting Temperature	160	°C	ASTM D 3418
Optical properties			
ASTM Data			
Haze	8	%	ASTM D 1003
Other properties			
Density	900	kg/m ³	ASTM D 792

Characteristics**Processing**

Injection Molding

Delivery form

Pellets, Natural Color

Additives

Release agent

Special Characteristics

High impact or impact modified, Transparent

Features

Color Stability, Random Copolymer

Certifications

Food contact, Food approval FDA 21 CFR

Regional Availability

North America, South and Central America